CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	CP-2022-04-25-26	Date: 23-03-22
Customer	:	Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.	
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.	
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.	
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.	
Customer's Reference	:	EE/DD/W.O/79/2021-22	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	19-03-22	
Sample Type /Size	:	Precast Cover Slab	
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete	
Date of test	:	19/03/2022	

AE-12

ಸಹಾಯಕ ಕಾರ್ಯ ನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.48	100.51	2.485	4474	119.9	26.8	24.9	31.2
2	Cover Slab-2	75.52	100.49	2.442	4478	125.7	28.1	26.1	32.6
3	Cover Slab-3	75.49	100.52	2.419	4475	122.5	27.4	25.5	31.8

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯ ನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL Pro Sl. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL| ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE KERB STONE

Date: 30-03-22

Lab ID	:	CP-2022-04-25-26
Customer	:	Assistant Executive Engineer.Shettyhalli Sub Division. BBMP. Bangalore.
Address	:	Shettyhalli Sub Division. BBMP. Bangalore.
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-03-22
Sample Type /Size	:	CC Kerb Stone/ 450*165*400mm
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete
Date of test	:	26/03/2022

AE-12
ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು ಎಸ್ಆರ
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	100.03	165.48	2.956	7857	151.2	19.2	19.2	24.1
2	B	100.03	165.52	2.944	7857	147.6	18.8	18.8	23.5
3	C	100.04	165.47	2.498	7859	152.4	19.4	19.4	24.2

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಅಭಿಯಂತರರು,
ವಾರ್ಡ್ ನಂ 12 ಶೆಟ್ಟಿಹಳ್ಳಿ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL PRO Sl. Date. BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2022-04-25-26** **Date: 23/03/2022**
Customer	:	Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-03-22
Customer ID	:	M25 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	23/03/2022

AE-12
ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರ
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	23/03/2022	149.76 X 151.91 X 150.34	22750	8.274	536.6	23.6	23.0
2	M25 Concrete	M25	16/03/2022	23/03/2022	151.38 X 149.52 X 151.29	22636	8.488	519.3	22.9	
3	M25 Concrete	M25	16/03/2022	23/03/2022	151.86 X 151.23 X 150.74	22966	8.311	516.5	22.5	

* The results obtained are satisfactory as per standard requirements

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ವಾರ್ಡ್ ನಂ 12, ಶೆಟ್ಟಿಹಳ್ಳಿ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL Pro Sr. Date. BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2022-04-25-26** **Date: 13/04/2022**
Customer	:	Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-03-22
Customer ID	:	M25 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	13/04/2022

AE-12
ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	13/04/2022	149.08 X 150.80 X 149.48	22481	8.952	635.2	28.3	28.3
2	M25 Concrete	M25	16/03/2022	13/04/2022	151.81 X 150.43 X 150.87	22838	8.339	646.2	28.3	
3	M25 Concrete	M25	16/03/2022	13/04/2022	151.82 X 150.57 X 149.32	22859	8.626	647.0	28.3	

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ವಾರ್ಡ್ ನಂ 12, ಶೆಟ್ಟಿಹಳ್ಳಿ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 23/03/2022

Lab ID	:	CP-2022-04-25-26
Customer	:	Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS). #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-03-22
Customer ID	:	M25 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	23/03/2022

AE-12
ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿ
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂ

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	23/03/2022	149.70 X 150.64 X 150.06	22552	8.414	519.7	23.0	22.8
2	M25 Concrete	M25	16/03/2022	23/03/2022	150.80 X 151.85 X 150.84	22899	8.400	516.4	22.6	
3	M25 Concrete	M25	16/03/2022	23/03/2022	149.60 X 149.12 X 149.92	22309	8.589	508.6	22.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ವಾರ್ಡ್ ನಂ 12, ಶೆಟ್ಟಿಹಳ್ಳಿ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2022-04-25-26** **Date: 13/04/2022**
Customer	:	Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-03-22
Customer ID	:	M25 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

AE - 12
ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Date of test : 13/04/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	13/04/2022	151.05 X 151.40 X 149.48	22870	9.020	642.4	28.1	28.1
2	M25 Concrete	M25	16/03/2022	13/04/2022	151.19 X 149.15 X 151.01	22549	8.650	622.2	27.6	
3	M25 Concrete	M25	16/03/2022	13/04/2022	149.37 X 150.64 X 150.62	22502	8.563	644.5	28.6	

* The results obtained are satisfactory as per standard requirements

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ವಾರ್ಡ್ ನಂ 12, ಶೆಟ್ಟಿಹಳ್ಳಿ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 23/03/2022

b ID	:	CP-2022-04-25-26
stomer	:	Assistant Executive Engineer,Shettyhalli Sub Division. BBMP, Bangalore.
ddress	:	Shettyhalli Sub Division. BBMP, Bangalore.
roject Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
gency	:	Sri KUMARA B J (K B CONSTRUCTIONS). #01. Sri nilaya. Behind Rangamandira. Devarabhavi Road. Bagalgunte. Nagasandra (P). Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-03-22
Customer ID	:	M25 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

AE-12
ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಕೆಬ್ಬಕಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Date of test : 23/03/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	23/03/2022	150.74 X 151.58 X 150.64	22849	8.810	533.2	23.3	22.9
2	M25 Concrete	M25	16/03/2022	23/03/2022	151.04 X 151.71 X 149.86	22914	8.897	531.0	23.2	
3	M25 Concrete	M25	16/03/2022	23/03/2022	149.40 X 151.70 X 151.12	22665	8.699	503.5	22.2	

* The results obtained are satisfactory as per standard requirements

Note:

The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 30 days from the date of issue of test certificate

ಸಹಾಯಕ ಅಭಿಯಂತರರು,
ವಾರ್ಡ್ ನಂ 12. ಶೆಟ್ಟಿಹಳ್ಳಿ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2022-04-25-26 **Date: 13/04/2022**

Customer : Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.

Address : Shettyhalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.

Agency : Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.

AE-12

Customer's Reference : EE/DD/W.O/79/2021-22

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-03-22

Customer ID : M25 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/04/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	13/04/2022	149.33 X 149.03 X 151.55	22255	8.104	635.1	28.5	28.4
2	M25 Concrete	M25	16/03/2022	13/04/2022	150.55 X 149.09 X 151.51	22445	8.603	627.7	28.0	
3	M25 Concrete	M25	16/03/2022	13/04/2022	150.14 X 151.35 X 151.98	22723	8.892	653.0	28.7	

* The results obtained are satisfactory as per standard requirements

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sl. No. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 23/03/2022

Lab ID	:	CP-2022-04-25-26
Customer	:	Assistant Executive Engineer,Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads Abbigere circe to Lakshmi temple and Surrounding area (Pipe line road) in Ward No 12 Shettyhalli.
Agency	:	Sri KUMARA B J (K B CONSTRUCTIONS), #01, Sri nilaya, Behind Rangamandira, Devarabhavi Road, Bagalgunte, Nagasandra (P), Bangalore- 560073.
Customer's Reference	:	EE/DD/W.O/79/2021-22
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-03-22
Customer ID	:	M25 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	23/03/2022

AE-12
ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ
ಬಿಬಿಎಂಪಿ, ಬೆಂಗಳೂರು

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Concrete	M25	16/03/2022	23/03/2022	151.54 X 150.36 X 149.14	22786	9.090	531.1	23.3	23.0
2	M25 Concrete	M25	16/03/2022	23/03/2022	149.83 X 151.59 X 150.14	22713	8.408	525.5	23.1	
3	M25 Concrete	M25	16/03/2022	23/03/2022	149.08 X 149.50 X 149.26	22288	8.407	504.7	22.6	

* The results obtained are satisfactory as per standard requirements

Note:

The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL PRO Seal BANGALORE

FOR CIVIL Pro.

R R ARTHIK RECHAN
Authorised Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES